



NC266-3



No Clean Liquid Flux

Features:

- Rosin and Resin Free
- Very Good Wetting
- Halide-Free
- Lead-Free and Tin-Lead Compatible

Description:

NC266-3 is a rosin-free, resin-free, halide-free, no-clean wave solder flux designed to enhance wetting and prevent bridging during the wave soldering process. NC266-3 offers an enhanced activity level, as well as lower surface tension than other no-clean flux chemistries. NC266-3 performs well with bare copper, solder coated and organic coated PWBs, leaving negligible post-process residues that are non-conductive and do not require cleaning. NC266-3 may be utilized with tin-lead and lead-free solder alloys.


Application:

- NC266-3 is formulated for application via spray. For spraying, NC266-3 is ready to use directly from its container, no thinning required. When spray fluxing, it is imperative that proper flux coverage and uniformity be achieved and maintained. A dry flux coating of 500 to 1500 micrograms per square inch is recommended as a starting point.
- When nitrogen sealed wave solder equipment is used, it is generally necessary to apply slightly more flux than normal as a result of excess drying due to the extended length of the equipment.
- Monitoring and controlling the acid number is recommended for maintaining the flux composition. The acid number should be maintained between 13.98-15.44 MG KOH/GRAM or 30– 32 drops using AIM’s N.020 Titration Kit.

Process Control:

Due to the low percentage of solids in this flux, control of specific gravity with automated equipment usually is found to be ineffective; therefore, control via titration is necessary. AIM’s Titration Kit has proven to be cost-effective, user friendly, quick and accurate. Titration should be carried out at least once an hour for flux foaming operations, or more often if large variances are found.

Thermal Profile:



RATE of RISE 2-3 °C / SEC MAX	PROGRESS THROUGH 66°C - 77°C (150 - 170°F)	PCB TOP SIDE TEMP 87°C - 115°C (190°F - 240°F)	COOLDOWN ≤ 4°C
	≤ 40 SECONDS	JUST BEFORE WAVE	

Cleaning:

NC266-3 can be cleaned, if necessary, with saponified water or an appropriate solvent cleaner. Please refer to the AIM No-Clean-Cleaner Matrix for a list of suitable cleaning materials.

Handling:

- NC266-3 has an unopened shelf life of 1 year when stored at room temperature.
- Do not store near fire or flame.
- Keep away from sunlight as it may degrade product.
- NC266-3 is shipped ready-to-use, no mixing necessary.
- Do not mix used and unused chemical in the same container.
- Reseal any opened containers.

Safety:

- Use with adequate ventilation and proper personal protective equipment.
- Refer to the accompanying Material Safety Data Sheet for any specific emergency information.
- Do not dispose of any hazardous materials in non-approved containers.

Physical Properties:

Parameter	Value
J-STD-004	ORL0
Visual	Clear, Colorless
Odor	Aromatic (Slightly)
Solids Content	2.4%
Acid Number	13.98 – 15.44 mg KOH per gram flux

Parameter	Value
Specific Gravity	0.78 – 0.80 (water = 1)
Flash Point	< 10°C
Boiling Point	82°C
pH (1% solution /water)	5.38 – 7.50

Corrosion Testing:

Parameter	Requirements	Results
Copper Mirror (24 hrs @ 25°C, 50%RH)	IPC-TM-650-2.3.32	Low
Halide Test (Silver Chromate)	IPC-TM-650-2.2.33	Pass

Surface Insulation Resistance:

Reference	Property	Pass-Fail Criteria	Results
IPC-TM-650 method 2.6.3.3 85°C / 85% R.H.	Control coupons	>1E+9 Ω at 96 and 168 hrs	9.17E+9 Ω and 7.53E+9 Ω Pass
	Sample coupons – pattern up	>1E+8 Ω at 96 and 168 hrs	1.01E+10 Ω and 8.33E+9 Ω Pass
	Sample coupons – pattern down	>1E+8 Ω at 96 and 168 hrs	6.34E+9 Ω and 5.61E+9 Ω Pass
	Post-test visual inspection	No dendrite growth or corrosion	Pass

Electromigration:

Test	Conditions	Specification	Results
Electromigration Bellcore GR-78 Flux Requirements	65°C/85% R.H. 500 hrs – Control	Rf/Ri > 0.1	Pass
	65°C/85% R.H. 500 hrs – Sample	Rf/Ri > 0.1	Pass

Canada +1-514-494-2000 · USA +1-401-463-5605 · Mexico +52-656-630-0032 · Europe +44-1737-222-258
 Asia-Pacific +86-755-2993-6487 · India +91-80-41554753 · info@aimsolder.com · www.aimsolder.com
 AIM IS ISO9001:2008 & ISO14001:2004 CERTIFIED

The information contained herein is based on data considered accurate and is offered at no charge. Product information is based upon the assumption of proper handling and operating conditions. All information pertaining to solder paste is produced with 45-micron powder. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please refer to <http://www.aimsolder.com/Home/TermsConditions.aspx> to review AIM's terms and conditions.